

SUPRA

BSM-50

HYBRID

**SILICA & ANTIMONY SELECTIVE
HYBRID STRONG BASE ANION
BORATE FORM**

ResinTech BSM-50 is a borate form antimony and silica selective hybrid gel type 1 strong base anion resin. Hydrated iron oxide is monoatomically dispersed through the polymer, giving the product hybrid properties. The borate form hybrid is able to remove chloride and sulfate in addition to silica, antimony-125, and other radionuclides. BSM-50 is stable and is intended for all nuclear applications such as spent fuel pools that contain borated water.

APPLICATIONS

- Antimony Removal
- Silica Removal

TYPICAL PROPERTIES & PHYSICAL CHARACTERISTICS

Polymer Matrix	Styrenic Gel
Ionic Form	Borate
Functional Group	Iron oxide Hybrid / Triethylamine
Physical Form	Spherical Beads
Particle Size	16 to 50 US Mesh (297 - 1190µm)
% < 50 mesh (300µm)	< 1%
Minimum Sphericity	95%
Uniformity Coefficient	1.6
Temp Limit	250°F (121°C)
Capacity (meq/mL)	1.4
Moisture Retention	35% to 50%
Shipping Weight	48 - 50 lbs/ft ³ (769 - 801 g/L)
Color	Black

PACKAGING OPTIONS

- 500 ml samples
- 1 ft³ bags
- 1 ft³ boxes
- 1 ft³ drums
- 7 ft³ drums
- 42 ft³ supersacks

Revision 1.1
© 2020 ResinTech, Inc.





SUPRA

BSM-50

HYBRID

**SILICA & ANTIMONY SELECTIVE
HYBRID STRONG BASE ANION
BORATE FORM**




SILICA REMOVAL

ResinTech BSM-50 can be used at moderate pH to remove silica. At a flow rate of 0.5 BV/min, removal efficiency of ninety percent is possible for several hundred bed volumes of throughput. Silica does not dump as the resin exhausts; silica leakage increases gradually but some removal continues for many thousands of additional bed volumes. Even though silica removal is not complete, the lowering of silica helps maintain purity in spent fuel pools and other radwaste systems.

ANTIMONY REMOVAL

Trace levels of antimony are adsorbed by the iron hybrid material inside ResinTech BSM-50, which in all other respects remains a strong base anion resin. The resin is typically used as the bottom layer of a multilayer exchange tank. Antimony removal reduction is typically around 90% and in recycle applications where the source of antimony has been removed, remaining antimony can be reduced below the limit of detection.

TYPICAL USE IS LAYERED UNDERNEATH OTHER MEDIAS



SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature	
Borate form	170°F
Minimum bed depth	6 to 12 inches
Maximum pressure loss	25 psi
Operating pH range	4 to 10 SU
Service flow rate	1 to 10 gpm/cu.ft.

Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums. For operation outside these guidelines, contact ResinTech Technical Support

Revision 1.1
© 2020 ResinTech, Inc.

